

Electronic structure of the orthorhombic and tetragonal phases of Tl_3PbBr_5

O.Y. Khyzhun^a, V.L. Bekenev^a, N.M. Denysyuk^a, M.V. Karpets^a, O.V. Parasyuk^b,
S.P. Danylchuk^c

^a*Institute for Problems of Materials Science, National Academy of Sciences of Ukraine, 3 Krzhyzhanivsky
Street, Kyiv 03142, Ukraine*

^b*Department of Inorganic and Physical Chemistry, Eastern European National University, 13 Voli
Avenue, Lutsk 43025, Ukraine*

^c*Department of Physics, Eastern European National University, 13 Voli Avenue, Lutsk 43025, Ukraine*

Trithallium lead pentabromide, Tl_3PbBr_5 , is recognized as a new low-phonon energy host material operating in mid-IR and far-IR regions. Two polymorphous forms, namely orthorhombic low-temperature (LT) and tetragonal high-temperature (HT), have been detected for this compound: the *LT*- Tl_3PbBr_5 phase crystallizes in the space group $P2_12_12_1$, with the lattice parameters $a = 15.397 \text{ \AA}$, $b = 9.061 \text{ \AA}$, and $c = 8.537 \text{ \AA}$, whilst the *HT*- Tl_3PbBr_5 phase possesses the lattice parameters $a = b = 15.486 \text{ \AA}$ and $c = 8.903 \text{ \AA}$ (space group $P4_1$). The non-central space groups adopted by both polymorphous forms of the Tl_3PbBr_5 compound make it a very prospective material for optoelectronics and non-linear optics devices (lasers, luminophors, narrow-band optical filters). In the present work, X-ray photoelectron core-level and valence-band spectra for pristine and Ar^+ -ion irradiated surfaces of a Tl_3PbBr_5 single crystal grown by the Bridgman-Stockbarger method have been measured. Our X-ray photoelectron spectroscopy (XPS) results reveal high chemical stability of Tl_3PbBr_5 single crystal surface. Total and partial densities of states of constituent atoms of the orthorhombic *LT*- Tl_3PbBr_5 and tetragonal *HT*- Tl_3PbBr_5 phases have been calculated using the first-principles full potential linearized augmented plane wave (FP-LAPW) method. The FP-LAPW data reveal that contributions of the Br 4p-like states dominate in the valence band of the both phases of Tl_3PbBr_5 ; they contribute mainly into the top and the central portion of the valence band with also significant contributions throughout the whole valence-band region. The bottom of the valence band of the orthorhombic and tetragonal phases of Tl_3PbBr_5 is composed mainly of the Tl 6s-like states. Additionally, the unoccupied Pb 6p- and Tl 6p-like states in almost equal proportion dominate at the bottom of the conduction band of *LT*- Tl_3PbBr_5 , whilst the unoccupied Pb 6p-like states are the dominant contributors at the bottom of the conduction band of the *HT*- Tl_3PbBr_5 phase. Our theoretical data reveal that the orthorhombic *LT*- Tl_3PbBr_5 and tetragonal *HT*- Tl_3PbBr_5 phases are indirect-gap materials with band gap of 3.05 and 2.26 eV, respectively. The theoretical predictions are confirmed by the XPS measurements carried out for the both phases of Tl_3PbBr_5 .